



24 Chestnut St., Carnegie, PA 15106
Phone: 412.276.6333 Fax: 412.276.7124

**New Shrinkage & Absorption Rates
Clays Made With 325 Mesh Custer Feldspar
As Of September 22, 2015**

Clay Number	Cone	Shrinkage Rate	Absorption Rate
112	6	12.5%	1.85%
153	6	12.5%	4.00%
153	10	14.0%	0.75%
240	6	13.5%	1.60%
257	8	14.0%	0.50%
257	10	15.0%	0.25%
259	6	13.0%	2.80%
259	10	14.0%	0.50%